



150900341277

检测报告/Test Report

报告编号: A2200030341101004E
Report No.:

第 1 页 共 4 页
Page 1 of 4

委托单位: 江阴市兴国食品包装涂料有限公司
Applicant: Jiangyin xingguo food packaging coating Co., LTD
地 址: 江阴市北国镇鉴青村朱家坝 5 号
Address: No.5 Zhu Jiaba, Jianqing Village, Beiguo Town, Jiang Yin city, Jiangsu, China

样品信息 / Report on the submitted sample said to be:

样品名称 Sample Name : 涂料/Coating
CTI 样品编号 CTI Sample No. : CM01420004
生产商 Manufacturer : 江阴市兴国食品包装涂料有限公司
Jiangyin xingguo food packaging coating Co., LTD
型号 Model No. : 2004-822/823
样品数量 Sample Quantity : 4pcs 双面涂布//Double coating
样品状态 Sample Status : 完好/Intact
样品接收日期 Sample Received Date : 2020/02/27
样品检测日期 Sample Tested Date : 2020/02/27~2020/04/01

检测部位描述 涂料/Coating

/ Test Part Description:

检测项目/ Test Item(s): 请参见下页。/ Please refer to the following page(s).

检测结果/ Test Result(s): 请参见下页。/ Please refer to the following page(s).

检测结论/Test Conclusion: 经检验, 所检项目符合 GB 9685-2016《食品安全国家标准 食品接触材料及制品用添加剂使用标准》标准规定的技术要求。/Upon testing, the test item(s) of the submitted sample(s) comply with GB 9685-2016.



编制: 朱胜男
Complued by: 朱胜男

审核: 计会敏
Reviewed by: 计会敏



批准: 吴秀宏
Approved by: 吴秀宏

日期: 2020/04/02
Date: 2020/04/02

吴秀宏 Alice
Technical director

检测报告/Test Report

报告编号: A2200030341101004E
Report No.:

第 2 页共 4 页
Page 2 of 4

检测结果:

Test Result(s):

序号 No.	检测项目 Test Item(s)	单位 Unit	检测结果 Test Result	检出限 DL	标准要求 Limit	结论 Conclusion	检测方法 Test Method
	双酚 A 特定迁移量 Specific migration of BPA						
1	去离子水, Deionized water 121 °C, 30min+40 °C, 10d	mg/kg	未检出 Absent	0.01	≤0.6	符合 Pass	GB 31604.10-2016
	4% 乙酸(体积分数), 4% acetic acid (v/v) 121 °C, 30min+40 °C, 10d	mg/kg	未检出 Absent	0.01	≤0.6	符合 Pass	GB 31604.10-2016

备注: 1. DL = 检出限。
2. 检测结果为第一次迁移试验的测定结果。
3. 模拟物及迁移实验条件由客户指定。
4. 样品实际使用过程中的面积体积比 S/V 未知, 按照标准要求 6dm²/1kg (L) 进行迁移试验和结果换算。

Note(s): 1. DL = Detection Limit.
2. The test result(s) is (are) the result(s) of the first migration test.
3. Test condition & simulant were specified by client.
4. The surface to volume ratio (S/V) in actual use is unknown, the migration test was carried out and the test result(s) was (were) converted according to 6 dm²/1kg (L) regulated in the standard.


检测报告/Test Report

报告编号: A2200030341101004E
Report No.:

第 3 页共 4 页
Page 3 of 4

样品图片

Photo(s) of the sample(s)



检测报告/Test Report

报告编号: A2200030341101004E
Report No.:

第 4 页共 4 页
Page 4 of 4

*** 报告结束 ***

*** End of report ***

注意:

Attention:

1. 报告无批准人签字、检验检测专用章及报告骑缝章, 或经涂改, 以及复印报告未加盖红色检验检测专用章均视作无效;

This report is considered invalidated in one or more of the following conditions: no approval signature; no testing seal of CTI; no cross-page seal; altered; a copy without the red testing seal of CTI.

2. 未经本公司批准, 不得部分复制本报告;

Without written approval of CTI, this report shall not be reproduced partly.

3. 样品信息由客户提供, 本报告检测结果仅对受检样品负责;

The sample Information is provided by the customer, and the results shown in this test report refer only to the sample(s) tested.

4. 不得擅自使用检测结果进行不当宣传;

Unauthorized use of the test results for improper publicity is impermissible.

5. 如果对检测结果有异议, 请于收到报告之日起 7 个工作日内提出, 逾期不予受理。

Objection to the test results should be raised within 7 working days from the date of receiving the report, otherwise it will not be accepted.

女
限
公
司